

Table of tank chemical resistance to some fluids and reagents

PRODUCT	°C		PRODUCT	°C		PRODUCT	°C		PRODUCT	°C	
	23°	60°		23°	60°		23°	60°		23°	60°
Acetic acid (10%)	R	R	Chloroform	LR	NR	Iron nitrate (ico)	R	R	Sodium benzoate (35%)	R	R
Acetic acid (50%)	R	LR	Chlorosulphonic acid (100%)	NR	NR	Iron sulphate (oso)	R	R	Sodium bicarbonate	R	R
Acetic aldehyde	LR	NR	Cider	R	R	Lead acetate	R	R	Sodium borate	R	R
Acetic anhydride	NR	NR	Citric acid (sat.)	R	R	Lead nitrate	R	R	Sodium bromide	R	R
Air	R	R	Coffee	R	R	Liquid chlorine	NR	NR	Sodium carbonate	R	R
Alcohol butilico	R	R	Cola concentrates	R	R	Liquids to develop photographs	R	R	Sodium chlorate	R	R
Alcohol from coconut oil	R	R	Copper chloride (sat.)	R	R	Lye (10%)	R	R	Sodium chloride	R	R
Alcool amilico	R	R	Copper cyanide (sat.)	R	R	Magnesium carbonate	R	R	Sodium cyanide	R	R
Alum (all types)	R	R	Copper fluoride (2%)	R	R	Magnesium chloride	R	R	Sodium dichromate	R	R
Aluminium chloride (all conc.)	R	R	Copper nitrate (sat.)	R	R	Magnesium hydroxide	R	R	Sodium disulphate	R	R
Aluminium fluoride (all conc.)	R	R	Copper sulphate (sat.)	R	R	Magnesium nitrate	R	R	Sodium disulphite	R	R
Aluminium sulphate (all conc.)	R	R	Corn oil	R	R	Magnesium sulphate	R	R	Sodium ferrocyanide	R	R
Amm. persulphate (sat. sol.)	R	R	Cotton oil	R	R	Mercury	R	R	Sodium fluoride	R	R
Ammonia (10% gas)	R	R	Dextrin	R	R	Methyl alcohol (100%)	R	R	Sodium hydroxide	R	R
Ammonium carbonate	R	R	Dextrose	R	R	Methylene chloride (100%)	LR	NR	Sodium hypochlorite	R	R
Ammonium chloride (sat. sol.)	R	R	Dextrose (sat. water sol.)	R	R	Milk	R	R	Sodium nitrate	R	R
Ammonium fluoride (sat. sol.)	R	R	Diazonium salts	R	R	Mineral oils	R	LR	Sodium phosphate (tri)	R	R
Ammonium hydrate (10%)	R	R	Dibutyl phthalate	LR	LR	Naphtha	LR	NR	Sodium sulphate	R	R
Ammonium hydrate (30%)	R	R	Dichlorobenzene (ortho and para)	NR	NR	Naphthalene	NR	NR	Sodium sulphide	R	R
Ammonium nitrate (sat. sol.)	R	R	Diesel for domestic use	LR	NR	n-Heptane	LR	LR	Solutions for brass plating	R	R
Ammonium sulphate (sat. sol.)	R	R	Diesel for motor vehicles	LR	LR	Nickel chloride	R	R	Solutions for cadmium plating	R	R
Amyl acetate	NR	NR	Diethyl chetone	LR	LR	Nickel nitrate	R	R	Solutions for copper plating	R	R
Amyl chloride	NR	NR	Diethylene glycol	R	R	Nickel sulphate	R	R	Solutions for gold plating	R	R
Aniline	NR	NR	Diglycolic acid	R	R	Nicotine (diluted)	R	R	Solutions for lead plating	R	R
Aqua-regia	NR	NR	Dimethylamine	NR	NR	Nitric acid (30%)	R	R	Solutions for nickel plating	R	R
Aromatic hydrocarbons	NR	NR	Disodium phosphate	R	R	Nitric acid (50%)	R	LR	Solutions for photography	R	R
Arsenic acid (all conc.)	R	R	Emulsifiers for photography	R	R	Nitric acid (70%)	R	LR	Solutions for silver plating	R	R
Ascorbic acid (10%)	R	R	Ethane dichloride	NR	NR	Nitric acid (95%)	NR	NR	Solutions for tin plating	R	R
Barium carbonate (sat. sol.)	R	R	Ethyl acetate	LR	NR	Nitrobenzene	NR	NR	Solutions for zinc plating	R	R
Barium chloride (sat. sol.)	R	R	Ethyl alcohol	R	R	n-Octane	R	R	Starch (saturated solution)	R	R
Barium hydrate	R	R	Ethyl alcohol (35%)	R	R	Olive oil	NR	NR	Stearic acid	R	R
Barium sulphate (sat. sol.)	R	R	Ethyl benzene	NR	NR	Oxalic acid	R	R	Sulphorous acid	R	R
Barium sulphide (sat. sol.)	R	R	Ethyl chloride	NR	NR	Perchloroethylene	NR	NR	Sulphuric acid (100%)	R	R
Beer	R	R	Ethyl ether	NR	NR	Petrol	NR	NR	Sulphuric acid (50%)	R	R
Benzene	NR	NR	Ethylene glycol	R	R	Potassium bicarbonate	R	R	Sulphuric acid (70%)	R	LR
Benzoic acid (all conc.)	R	R	Ethylene trichloride	NR	NR	Potassium bromide	R	R	Sulphuric acid (80%)	R	NR
Bismuth carbonate (sat. sol.)	R	R	Fluoboric acid	R	R	Potassium carbonate	R	R	Sulphuric acid (96%)	LR	NR
Borax	R	R	Fluosilicic acid	R	LR	Potassium chlorate	R	R	Sulphuric acid (98%)	LR	NR
Boric acid (all conc.)	R	R	Fluosilicic acid (30%)	R	R	Potassium chloride	R	R	Tannic acid	R	R
Boron tetrafluoride	R	R	Formic acid (all conc.)	R	R	Potassium chromate (40%)	R	R	Tetrahydrofuran	LR	NR
Brine	R	R	Fructose	R	R	Potassium cyanide	R	R	Tin chloride (ico)	R	R
Bromium (liquid)	NR	NR	Fruit pulp	R	R	Potassium dichromate (40%)	R	R	Tin chloride (oso)	R	R
Butanediol (10%)	R	R	Furfurolo	NR	NR	Potassium ferrocyanide II	R	R	Titanium tetrachloride	NR	NR
Butanediol (100%)	R	R	Furfuryl alcohol	LR	LR	Potassium ferrocyanide III	R	R	Toluene	LR	LR
Butanediol (50%)	R	R	Gallic acid	R	R	Potassium fluoride	R	R	Triethylene glycol	R	R
Butyl acetate	NR	NR	Glucose	R	R	Potassium hydroxide (conc.)	R	R	Turpentine	LR	LR
Butyric acid (all conc.)	NR	NR	Glycerol	R	R	Potassium nitrate	R	R	Urea (30%)	R	R
Calcium carbonate (sat. sol.)	R	R	Glycol	R	R	Potassium perchlorate (10%)	R	R	Vanilla	R	R
Calcium chlorate (sat. sol.)	R	R	Glycolic acid	R	R	Potassium permanganate (20%)	R	R	Vinegar	R	R
Calcium chloride (sat. sol.)	R	R	Hexachlorobenzene	R	R	Potassium persulphate	R	R	Water	R	R
Calcium disulphite	R	R	Hexanol (commercial)	R	R	Potassium sulphate (conc.)	R	R	Wetting agent	R	R
Calcium hydrate (all conc.)	R	R	Hydrochloric acid (all conc.)	R	R	Potassium sulphide (conc.)	R	R	Whisky	R	R
Calcium nitrate (50%)	R	R	Hydrochloric acid (dry gas)	R	R	Potassium sulphite (conc.)	R	R	Wine	R	R
Calcium oxide (sat. sol.)	R	R	Hydrocyanic acid	R	R	Propargyl alcohol	R	R	Xylene	NR	NR
Calcium sulphate	R	R	Hydrogen	R	R	Propyl alcohol	R	R	Yeast	R	R
Camphor oil	LR	NR	Hydrogen bromide (50%)	R	R	Propylene dichloride (100%)	NR	NR	Zinc bromide	R	R
Carbon dioxide	R	R	Hydrogen fluoride (40%)	R	R	Propylene glycol	R	R	Zinc carbonate	R	R
Carbon oxide (all conc.)	R	R	Hydrogen fluoride (60%)	R	R	Pyridine	R	R	Zinc chloride	R	R
Carbon sulphide	NR	NR	Hydrogen sulphide	R	R	Resorcinol	R	R	Zinc oxide	R	R
Carbon tetrachloride	LR	NR	Hydroquinone	R	R	Salicilic acid	R	R			
Carboxic acid	R	R	Hypochlorous acid	R	R	Seawater	R	R			
Castor oil (all conc.)	R	R	Ink	R	R	Selenic acid	R	R			
Chlorine (100% dry gas)	LR	NR	Iodine (sol. in KJ)	LR	NR	Silver nitrate (sol.)	R	R			
Chlorine water (sat. sol. 2%)	R	R	Iron chloride (ico)	R	R	Soap solution (all conc.)	R	R			
Chlorobenzene	NR	NR	Iron chloride (oso)	R	R	Sodium acetate	R	R			

R = Resistant **LR** = Limited resistance **NR** = No-resistance

For information on compatibility for containment of fluids and reagents other than water, it is compulsory to ask for information and approval from the technical office.

For use with liquids other than water, remember to take into consideration any differences in specific weight.

* The tanks do not have Fire Brigade certification to contain diesel/gasoline fuel.

For use with liquids and fluids other than water, comply with local standards in force for environment and safety requirements.

ELBI guarantees resistance of its PLASTO tanks to liquids declared suitable (R) in the table.

Maintaining the characteristics of the liquids contained inside of PLASTO tanks should be checked by and is the responsibility of the user.

Standard accessories for water

- Connections:

A. with threaded holes

B. with joints: (Fig. 1)

- drainage (3/4")

- inlet (dn 1) and overflow (dn 1) in PP with ring nut and gasket;

- Hole ø 28 for float




Figure 1